

ASA LI913

Extrusion Molding

Description

Good Weatherability, High Impact

Application

Satellite Antena, Boat, Lamp Cover, Door Frame,
Electronic Components

Properties	Test Condition	Test Method	Unit	Typical Value
Physical				
Specific Gravity		ASTM D792	-	1.07
Molding Shrinkage (Flow), 3.2mm		ASTM D955	%	0.4~0.7
Melt Flow Rate	220℃/10kg	ASTM D1238	g/10min	6
Mechanical				
Tensile Strength, 3.2mm		ASTM D638		
@ Yield	50mm/min		kg/cm ²	410
Tensile Elongation, 3.2mm		ASTM D638		
@ Yield	50mm/min		%	>5
@ Break	50mm/min		%	35
Tensile Modulus, 3.2mm	1mm/min	ASTM D638	kg/cm ²	17,600
Flexural Strength, 3.2mm	15mm/min	ASTM D790	kg/cm ²	660
Flexural Modulus, 3.2mm	15mm/min	ASTM D790	kg/cm ²	19,500
IZOD Impact Strength, 6.4mm (Notched)	23℃	ASTM D256	kg·cm/cm	35
	-30℃		kg·cm/cm	6
IZOD Impact Strength, 3.2mm (Notched)	23℃	ASTM D256	kg·cm/cm	45
	-30℃		kg·cm/cm	6
Rockwell Hardness	R-Scale	ASTM D785	-	93
Thermal				
Heat Deflection Temperature, 6.4mm (Unannealed)	18.6kg	ASTM D648	℃	86
	4.6kg		℃	96
Vicat Softening Temperature	5kg, 50℃/h	ASTM D1525	℃	94
Flammability		UL94		
0.8mm			class	
1.6mm			class	HB
2.5mm			class	
3.2mm			class	HB
Relative Temperature Index		UL 746B		
Electrical			℃	
Mechanical with Impact			℃	
Mechanical without Impact			℃	

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection molulded specimens and after 48 hours storage at 23℃, 50% relative humidity.

ASA LI913

Extrusion Molding

Description

Good Weatherability, High Impact

Application

Satellite Antena, Boat, Lamp Cover, Door Frame,
Electronic Components

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

ASA LI913

Extrusion Molding

Description

Good Weatherability, High Impact

Application

Satellite Antena, Boat, Lamp Cover, Door Frame, Electronic Components

Processing Guide (Extrusion Molding)

Processing Parameters		Unit	Value
Drying Temperature		℃	80 ~ 90
Drying Time		hrs	2 ~ 3
Minimum Moisture Content		%	0.01
Melt Temperature		℃	200 ~ 230
Barrel Temperature	Zone 1	℃	190 ~ 200
	Zone 2	℃	200 ~ 220
	Zone 3	℃	210 ~ 230
	Zone 4	℃	210 ~ 230
Adapter Temperature		℃	210 ~ 230
Die Temperature		℃	210 ~ 250
Roll Stack Temperature	Top	℃	70 ~ 90
	Middle	℃	70 ~ 90
	Bottom	℃	70 ~ 100

Note) Recommend initial lower temperatures settings to avoid material degradation/hang-up in die & purge material from extruder prior to shutdown.

ASA LI913

Extrusion Molding

Description

Good Weatherability, High Impact

Application

Satellite Antena, Boat, Lamp Cover, Door Frame,
Electronic Components

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.