

## < Specification Data >

### Polycarbonate Resin "Iupilon S-2001R"

- \* basic grades with releasing agent
- \* medium viscosity
- \* FDA



**MEP Europe GmbH**  
 Mitsubishi Engineering-Plastics Corp.  
 Prinzenalle 13  
 D-40549 Düsseldorf  
 Germany  
 Tel: 0049-(0)211-52392-51  
 Fax: 0049-(0)211-591272

Properties	Test Methods	Units	Values
<b>Physical Properties</b>			
Density	ISO 1183	g/cm <sup>3</sup>	1.20
Water Absorption (23°C, Underwater)		%	0.24
<b>Rheological Properties</b>			
Melt Volume-flow Rate (300°C, 1.2kg)	ISO 1133	cm <sup>3</sup> /10min	11
Molding Shrinkage (3.2mmt) (MD)		%	0.5-0.7
(TD)			0.5-0.7
<b>Mechanical Properties</b>			
Tensile Modulus	ISO 527-1	MPa	2400
Yield Stress	ISO 527-2		61
Yield Strain		%	5.6
Flexural Strength	ISO 178	Mpa	93
Flexural Modulus			2300
Charpy Impact Strength (23°C)	ISO 179-1	kJ/m <sup>2</sup>	NB
Charpy Notched Impact Strength (23°C)	ISO 179-2		76
<b>Thermal Properties</b>			
Temperature of Deflection Under Load (1.80MPa)	ISO 75-1	°C	129
	(0.45MPa)		ISO 75-2
Coefficient of Linear Thermal Expansion (MD)	ISO 11359-2	1/°C	6.5E-5
			(TD)

All data in this table are typical values obtained under MEP's standard test methods, and may not be applicable for those which are used under different conditions. These are not intended for warranty of customer's production achievement.