

# LUPOY GN5007FL

Injection Molding, PC/ABS, Cl/Br Free Flame Retardancy

## Application

Auto, Electronics, Home Appliances, Industrial Goods

Properties	Condition	Method	Unit	Typical Value
<b>Physical</b>				
Specific Gravity	23°C	ISO 1183		1.19
Shrinkage		ISO 294-4		
Flow	2.0mm		%	0.5~0.8
Cross-flow	2.0mm		%	0.6~0.9
Melt Flow Rate	250°C, 2.16kg	ISO 1133	g/10min	8.5
Water Absorption	23°C, 50% RH, 24hr	ISO 62	%	0.20
<b>Mechanical</b>				
Tensile Strength		ISO 527		
@Yield	4.0mm, 50mm/min		MPa	60
@Break	4.0mm, 50mm/min		MPa	64
Tensile Elongation		ISO 527		
@Yield	4.0mm, 50mm/min		%	5.0
@Break	4.0mm, 50mm/min		%	100
Tensile Modulus	4.0mm, 1.0mm/min	ISO 527	MPa	2,470
Flexural Strength	4.0mm, 2.0mm/min	ISO 178	MPa	93
Flexural Modulus	4.0mm, 2.0mm/min	ISO 178	MPa	2,280
IZOD Impact Strength		ISO 180		
4.0mm, Notched	23°C		kJ/m <sup>2</sup>	48
	-30°C		kJ/m <sup>2</sup>	12
	-40°C		kJ/m <sup>2</sup>	12
Charpy Impact Strength		ISO 179		
4.0mm, Notched	23°C		kJ/m <sup>2</sup>	51
	-30°C		kJ/m <sup>2</sup>	14
	-40°C		kJ/m <sup>2</sup>	11
Rockwell Hardness	R-Scale	ISO 2039		124
Shore Hardness		ISO 48-4		
Shore D	15s			
<b>Thermal</b>				
Melt Temperature	Peak	ISO 11357-3	°C	
Heat Deflection Temperature		ISO 75		
0.45MPa	4.0mm, Flatwise Unannealed		°C	124
1.8MPa	4.0mm, Flatwise Unannealed		°C	110
Vicat Softening Temperature	50N, 50°C/hr	ISO 306	°C	130
Coefficient of Linear Thermal Expansion		ISO 11359		
Flow	-30°C ~ 80°C		10 <sup>-6</sup> m/m·°C	85
Cross-flow	-30°C ~ 80°C		10 <sup>-6</sup> m/m·°C	77
Thermal Conductivity		ASTM E1461		
In-plane			W/m-K	
Through-plane			W/m-K	

## Flammability

Flammability		UL94	mm, Class	1.50mm, V-0
Relative Temperature Index(RTI)		UL746B		
Electrical	Min. Thickness		mm	1.50
	Temp		°C	95
	Max. Temp		°C	95
Mechanical With Impact	Thickness		mm	1.50
	Min. Thickness		mm	1.50
	Temp		°C	90
Mechanical Without Impact	Max. Temp		°C	90
	Thickness		mm	1.50
	Min. Thickness		mm	1.50
	Temp		°C	95
	Max. Temp		°C	95
	Thickness		mm	1.50

## Electrical

Comparative Tracking Index(CTI)	Solution A	UL746A	PLC	3
Surface Resistivity	23°C	IEC60093	Ohm	1E+15
Volume Resistivity	23°C	IEC60093	Ohm·m	1E+15
Dielectric Constant	23°C	ASTM D150		2.8
Dielectric Strength	23°C, 2.0mm	ASTM D149	kV/mm	18
EMI Shield	1GHz, 3.0mm	ASTM D4935	dB	

Note) Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow rate are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

Issued Date : 2022-08-01

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

# LUPOY GN5007FL

Injection Molding, PC/ABS, Cl/Br Free Flame Retardancy

## Application

Auto, Electronics, Home Appliances, Industrial Goods

### Processing Conditions (Injection Molding)

Processing Parameters	Unit	Value	
Drying Temperature	°C	90~100	
Drying Time	hrs	3~5	
Maximum Moisture Content	%	0.02	
Melt Temperature	°C	270~300	
Cylinder Temperature	Rear	°C	260~300
	Middle	°C	250 ~ 290
	Front	°C	250 ~ 270
Nozzle Temperature	°C	260 ~ 290	
Mold Temperature	°C	60 ~ 90	

Note) These guides may not apply directly or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding and so on.