

## TARNOFORM® 300 CE - POM

Restricted Grade. Please contact your Celanese representative for further information.

### Description

Tarnoform® 300 CE NATURAL is a medium viscosity polymer providing good performance in general purpose injection molding and extrusion. This grade provides overall excellent performance in many applications. Chemical abbreviation according to ISO 1043-1 >POM< Complies with EU 10/2011 and FDA CFR21 food contact regulations.

Physical properties	Value	Unit	Test Standard
Density	1410	kg/m³	ISO 1183
Melt volume rate, MVR	8	cm³/10min	ISO 1133
MVR temperature	190	°C	ISO 1133
MVR load	2,16	kg	ISO 1133
Molding shrinkage, parallel (flow)	2,0	%	ISO 294-4, 2577
Molding shrinkage, transverse normal	1,9	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	2800	MPa	ISO 527-2/1A
Tensile stress at yield, 50mm/min	62	MPa	ISO 527-2/1A
Tensile strain at yield, 50mm/min	10	%	ISO 527-2/1A
Flexural modulus, 23 °C	2500	MPa	ISO 178
Charpy impact strength, 23 °C	200	kJ/m²	ISO 179/1eU
Charpy notched impact strength, 23 °C	6	kJ/m²	ISO 179/1eA
Charpy notched impact strength, -30 °C	5,5	kJ/m²	ISO 179/1eA
Ball indentation hardness, 30s	144	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
Melting temperature, 10 °C/min	166	°C	ISO 11357-1/-3
DTUL at 1.8 MPa	104	°C	ISO 75-1, -2
DTUL at 0.45 MPa	155	°C	ISO 75-1, -2
Coeff. of linear therm expansion, parallel	1,2	E-4/°C	ISO 11359-2
Coeff. of linear therm expansion, normal	1,2	E-4/°C	ISO 11359-2

Electrical properties	Value	Unit	Test Standard
Volume resistivity	1E12	Ohm*m	IEC 60093
Surface resistivity	1E15	Ohm	IEC 60093
Electric strength	25	kV/mm	IEC 60243-1

### Typical injection moulding processing conditions

Pre Drying	Value	Unit	Test Standard
Drying time	3 - 4	h	-
Drying temperature	100 - 120	°C	-
Temperature	Value	Unit	Test Standard
Zone1 temperature	170 - 180	°C	-
Zone2 temperature	180 - 190	°C	-
Zone3 temperature	180 - 190	°C	-
Zone4 temperature	190 - 200	°C	-
Nozzle temperature	190 - 200	°C	-
Melt temperature	180 - 200	°C	-
Mold temperature	80 - 120	°C	-
Hot runner temperature	180 - 200	°C	-
Pressure	Value	Unit	Test Standard
Back pressure max.	40	bar	-
Speed	Value	Unit	Test Standard
Injection speed	slow-medium	-	-
Other	Value	Unit	Test Standard
Flow temperature	174	°C	Internal

### Other text information

---

## TARNOFORM® 300 CE - POM

Restricted Grade. Please contact your Celanese representative for further information.

---

### Pre-drying

Drying is not normally required. If material has come in contact with moisture through improper storage or handling or through regrind use, drying may be necessary to prevent splay and odor problems.

### Characteristics

---

#### Product Categories

Unfilled

#### Delivery Form

Pellets

#### Processing

Calendering, Film extrusion, Injection molding, Other extrusion, Profile extrusion, Sheet extrusion

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

### Contact Information

---

#### Americas

8040 Dixie Highway  
Florence, KY 41042 USA  
Product Information Service  
t: +1-800-833-4882  
t: +1-859-372-3244  
Customer Service  
t: +1-800-526-4960  
t: +1-859-372-3214  
e: info-engineeredmaterials-am@celanese.com

#### Asia

4560 Jinke Road  
Zhang Jiang Hi Tech Park  
Shanghai 201210 PRC  
Customer Service  
t: +86 21 3861 9288  
e: info-engineeredmaterials-  
asia@celanese.com

#### Europe

Am Unisys-Park 1  
65843 Sulzbach, Germany  
Product Information Service  
t: +49-800-86427-531  
t: +49-(0)-69-45009-1011  
e: info-engineeredmaterials-eu@celanese.com

### General Disclaimer

---

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products. The products mentioned herein are not intended for use in medical or dental implants.

### Trademark

---

© 2021 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.