



## TECHNICAL DATA SHEET

<b>Product</b>	<b>P 70G</b>
<b>Gruppo✓ Group</b>	<b>Plastificati Flexible</b>
<b>Categoria✓ Categorie</b>	<b>Stampaggio Articoli Tecnici Technical Articles Injection Moulding</b>
Emissione: 1 del 09/2016    Revisione: 1 del 10/2017    Stato: <b>Released</b>	

TECHNICAL INFORMATION	TESTING METHOD	UNIT OF MEASURE	VALUE
<b>Peso Specifico</b> Specific Weight	ISO 1183-1	g/cm <sup>3</sup>	1,300
<b>Durezza</b> Hardness	ISO 868	Shore A	75(PI) - 71(PV)
<b>Carico di Rottura</b> Tensile Strength	ISO 527	N/mm <sup>2</sup>	13
<b>Allungamento a Rottura</b> Elongation at Break	ISO 527	%	300
<b>Temp. di Irrig. a Torsione</b> Cold Flex	ISO 458	°C	- 30
<b>Stabilità Termica</b> Heat Stability	CEI 20-34/3-2	Minutes	
<b>Applicazioni</b>	Compound stampaggio calzature e articoli vari (con materiale da riciclo). Esente DEHP. Classificato antifiamma classe B2 secondo norma DIN 4102 (test interno su spessore 1,3 mm).		
<b>Note</b>	Le caratteristiche tecniche sopra riportate derivano da nostre analisi di laboratorio su campioni rappresentativi e sono da considerarsi valori medi tipici misurati sul prodotto e non possono essere usati come valori di specifica. Analisi eseguite su prodotto naturale non colorato.		
<b>Applications</b>	Compound for footwear and general purpose articles injection moulding (with recycle material). DEHP free. Classified as flame retardant class B2 according to DIN 4102 (internal test on a thickness of 1,3 mm).		
<b>Notes</b>	The above mentioned technical characteristics come from our laboratory tests done on representative samples. They have to be considered as average typical values measured on the product and can not be used as technical specification values. Analyses referred to natural material without pigments.		